



TPC 65A

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTIES

POLYETHER BASED ELASTOMER

| | |
|--|-------|
| HARDNESS SHORE A _____ | 62-67 |
| TENSILE PSI _____ | 2640 |
| 100% MODULUS PSI _____ | 280 |
| 300% MODULUS PSI _____ | 645 |
| ELONGATION % _____ | 440 |
| DIE C TEAR PLI _____ | 180 |
| BASHORE REBOUND _____ | 7 |
| COMPRESSION SET% _____ (METHOD B, 22 hrs @ 158°F) | 6 |