



TPC 8000A

TYPICAL PHYSICAL PROPERTIES

Hardness, Shore A _____	80-83
Tensile, psi (Mpa) _____	5000 (28.3)
Elongation, % _____	490
100% Modulus, psi (Mpa) _____	800 (5.5)
300% Modulus, psi (Mpa) _____	1500 (10.3)
D-470 Split Tear, pli (kN/m) _____	75 (13.1)
Die C Tear, pli (kN/m) _____	530 (92.8)
Bashore Rebound, % _____	58
Compression Set, Method B	
22 Hrs. @ 158 F (70 C) _____	25
Compressive Modulus, psi (Mpa)	
@ 5% _____	.210 (1.4)
@ 10% _____	.350 (2.4)
@ 15% _____	.490 (3.4)
@ 20% _____	.680 (4.7)
@ 25% _____	.940 (6.5)
Specific Gravity _____	1.07