



# TPC 9500A

## TYPICAL PHYSICAL PROPERTIES

<b>HARDNESS SHORE A</b>	<b>93-97</b>
<b>TENSILE PSI</b>	<b>7340</b>
<b>100% MODULUS PSI</b>	<b>2010</b>
<b>300% MODULUS PSI</b>	<b>4100</b>
<b>ELONGATION %</b>	<b>415</b>
<b>DIE C TEAR PLI</b>	<b>575</b>
<b>SPLIT TEAR PLI</b>	<b>205</b>
<b>COMPRESSION SET (METHOD B) %</b>	<b>30</b>
<b>CURED DENSITY g/cm<sup>3</sup></b>	<b>1.09</b>
<b>REBOUND %</b>	<b>42</b>
<b>COMPRESSION /DEFLECTION PSI</b>	
<b>5%</b>	<b>168</b>
<b>10%</b>	<b>598</b>
<b>15%</b>	<b>1004</b>
<b>25%</b>	<b>1558</b>
<b>LINEAR SHRINKAGE %</b>	<b>1.127</b>